



2239

Version No.4

Revision Date: 30/10/2024

Page 1 of 2

DESCRIPTION

2239 is an extruded butyl tape.

KEY FEATURES

Good adhesion to a wide range of substrates.

Good UV resistance.

The softer composition makes this product highly conformable.

Easy and accurate to use with little waste and no mess.

High tack.

Remains flexible throughout its service life.

USES

For use as an air, dust or water seal for compression joints and seams.

For water sealing applications in vehicle construction.

For fixing ridge tile flashing / membranes

PERFORMANCE

	UNIT	NOMINAL VALUE	TEST METHOD
Dynamic Tensile Adhesion	N/cm ²	18	H5
Dynamic Shear Adhesion	N/cm ²	14	H15
90° Peel Adhesion	N/cm	7	H48
180° Peel Adhesion	N/cm	11	H41
Specific Gravity	g/cm ³	1.65	H6
Moisture Vapour Transmission Rate	g/m ² /24hr/mm	0.24	ISO9932 / BS ISO 15106
Service Temperature Range	°C	-40 to +90	

H – HS Butyl Test Method

IMPORTANT: Information, specifications, procedures and recommendations provided (“information”) are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is user’s sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. The user is advised to review the specific context of the intended use to determine whether the user’s intended use violates any law or infringes upon any patent(s). No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

Gordleton Industrial Park,
Hannah Way, Sway Road,
Lymington, Hampshire,
SO41 8JD. UK.



T: +44 (0)1590 684400
F: +44 (0)1590 683728
E: sales@hsbutyl.com
W: www.hsbutyl.com



2239

Version No.4

Revision Date: 30/10/2024

Page 2 of 2

APPLICATION

PROPERTIES

Application temperature range: +5°C to +40°C

Shelf life: 24 months when stored flat in original packaging in cool, dry conditions.

INSTRUCTIONS

Surface preparation: All surfaces should be clean, dry and free from frost, grease and loose materials. When cleaning contaminated substrates, HS Butyl recommend that propan-2-ol (IPA) is used and allowed to dry prior to the application of the butyl tape.

Application: Apply direct from the reel onto one surface and press sufficiently along its whole length to achieve good initial adhesion. Remove backing paper and offer other surface to the butyl tape and push firmly to seal across the joint. The use of a roller to roll the joint, using firm pressure, is recommended to get a good bond.

PACKAGING

The product is normally supplied as an extruded strip on a siliconised release paper. A wide range of dimensions can be supplied. Product dimensions will determine the number of rolls per carton.

Available colours: Black, grey and white.

TOLERANCES

Rectangular sections:

Thickness $\pm 10\%$

Width: up to 25mm ± 1 mm

26mm to 100mm ± 2 mm

Bead sections:

Thickness $\pm 10\%$

Width $\pm 10\%$

GENERAL

2239 is part of a range of butyl products for Construction & Automotive markets. For further information, please contact our Customer Care Team or visit our Website.

NOTE TO USER: *by ordering/receiving product you accept the H.B. Fuller Conditions of Sale applicable in the region. Please request a copy if you have not received these or follow the link here: <https://www.hbfuller.com/en/about-us/conditions-of-sale>. These Conditions contain limits of liability and disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose). All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.*

Gordleton Industrial Park,
Hannah Way, Sway Road,
Lyminster, Hampshire,
SO41 8JD. UK.



T: +44 (0)1590 684400
F: +44 (0)1590 683728
E: sales@hsbutyl.com
W: www.hsbutyl.com